





F-19-1









(a) -brake value, 用紙厚さ(μm) 58 7 80 4 196 1

thickness

(b)

M '1 ~ '1' \		氏厚さ80 µ m)
用紙幅(学	eh > y	設定値
6		1
11		8
18	3	4

-traca brake value
F19-8

(c)

Mideness numidity (用紙厚さ80 µ m)	
湿度(%)	設定値(
80	6
65	4
15	8




Fig- 9.




Fig.10






Fig. 1/





This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

□ BLACK BORDERS
□ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
□ FADED TEXT OR DRAWING
□ BLURRED OR ILLEGIBLE TEXT OR DRAWING
□ SKEWED/SLANTED IMAGES
□ COLOR OR BLACK AND WHITE PHOTOGRAPHS
□ GRAY SCALE DOCUMENTS
□ LINES OR MARKS ON ORIGINAL DOCUMENT
□ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.